

NHG低熔点玻璃模压前后谱线折射率对照参考表

| 牌号 | 分类 | nA' | nr | nC | nC' | nHe-Ne | nD | nd | ne | nF | nF' | ng | nh | ni |
|--------|-----|---------|---------|---------|---------|---------|---------|----------------|---------|---------|---------|---------|---------|---------|
| | | 768.19 | 706.52 | 656.27 | 643.85 | 632.8 | 589.29 | 587.56 | 546.07 | 486.13 | 479.99 | 435.84 | 404.66 | 365.01 |
| D-PK60 | 模压前 | 1.58765 | 1.58923 | 1.59078 | 1.59121 | 1.59162 | 1.59341 | 1.59349 | 1.59561 | 1.59964 | 1.60014 | 1.60439 | 1.60831 | 1.61494 |
| | 模压后 | 1.58456 | 1.58614 | 1.58769 | 1.58812 | 1.58853 | 1.59032 | 1.59038 | 1.59250 | 1.59654 | 1.59704 | 1.60129 | 1.60521 | 1.61184 |
| D-FK61 | 模压前 | 1.49301 | 1.49407 | 1.49514 | 1.49543 | 1.49571 | 1.49694 | 1.49700 | 1.49845 | 1.50123 | 1.50157 | 1.50451 | 1.50721 | 1.51173 |
| | 模压后 | 1.49184 | 1.49290 | 1.49397 | 1.49426 | 1.49454 | 1.49577 | 1.49581 | 1.49726 | 1.50005 | 1.50039 | 1.50331 | 1.50601 | 1.51053 |
| H-FK69 | 模压前 | 1.58723 | 1.58873 | 1.59021 | 1.59062 | 1.59101 | 1.59275 | 1.59282 | 1.59489 | 1.59884 | 1.59934 | 1.60354 | 1.60740 | 1.61397 |
| | 模压后 | 1.58445 | 1.58595 | 1.58743 | 1.58784 | 1.58823 | 1.58997 | 1.58998 | 1.59205 | 1.59599 | 1.59649 | 1.60068 | 1.60454 | 1.61111 |
| D-FK95 | 模压前 | 1.43396 | 1.43478 | 1.43559 | 1.43582 | 1.43603 | 1.43696 | 1.43700 | 1.43810 | 1.44019 | 1.44044 | 1.44264 | 1.44466 | 1.44803 |
| | 模压后 | 1.43317 | 1.43399 | 1.43480 | 1.43503 | 1.43524 | 1.43617 | 1.43620 | 1.43730 | 1.43941 | 1.43966 | 1.44184 | 1.44386 | 1.44723 |
| D-ZK2N | 模压前 | 1.58054 | 1.58227 | 1.58399 | 1.58446 | 1.58491 | 1.58691 | 1.58700 | 1.58935 | 1.59384 | 1.59439 | 1.59917 | 1.60363 | 1.61145 |
| | 模压后 | 1.57867 | 1.58040 | 1.58212 | 1.58259 | 1.58304 | 1.58504 | 1.58512 | 1.58747 | 1.59196 | 1.59251 | 1.59731 | 1.60177 | 1.60959 |
| D-ZK3L | 模压前 | 1.58274 | 1.58447 | 1.58618 | 1.58665 | 1.58709 | 1.58905 | 1.58913 | 1.59142 | 1.59580 | 1.59634 | 1.60096 | 1.60523 | 1.61246 |
| | 模压后 | 1.58068 | 1.58241 | 1.58412 | 1.58459 | 1.58503 | 1.58699 | 1.58706 | 1.58935 | 1.59373 | 1.59427 | 1.59890 | 1.60317 | 1.61040 |
| D-ZK50 | 模压前 | 1.60194 | 1.60380 | 1.60565 | 1.60616 | 1.60664 | 1.60876 | 1.60886 | 1.61136 | 1.61616 | 1.61676 | 1.62184 | 1.62655 | 1.63460 |
| | 模压后 | 1.59974 | 1.60160 | 1.60345 | 1.60396 | 1.60444 | 1.60656 | 1.60666 | 1.60916 | 1.61395 | 1.61455 | 1.61965 | 1.62436 | 1.63241 |
| D-K9 | 模压前 | 1.51094 | 1.51241 | 1.51384 | 1.51424 | 1.51461 | 1.51625 | 1.51633 | 1.51825 | 1.52190 | 1.52236 | 1.52621 | 1.52976 | 1.53574 |
| | 模压后 | 1.50975 | 1.51122 | 1.51265 | 1.51305 | 1.51342 | 1.51506 | 1.51511 | 1.51703 | 1.52069 | 1.52115 | 1.52503 | 1.52858 | 1.53456 |
| D-LaK6 | 模压前 | 1.68502 | 1.68729 | 1.68955 | 1.69017 | 1.69076 | 1.69338 | 1.69350 | 1.69661 | 1.70258 | 1.70333 | 1.70974 | 1.71572 | 1.72593 |
| | 模压后 | 1.68233 | 1.68460 | 1.68686 | 1.68748 | 1.68807 | 1.69069 | 1.69081 | 1.69392 | 1.69988 | 1.70063 | 1.70704 | 1.71302 | 1.72323 |

NHG低熔点玻璃模压前后谱线折射率对照参考表

| 牌号 | 分类 | nA' | nr | nC | nC' | nHe-Ne | nD | nd | ne | nF | nF' | ng | nh | ni |
|----------------|-----|---------|---------|---------|---------|---------|---------|----------------|---------|---------|---------|---------|---------|---------|
| | | 768.19 | 706.52 | 656.27 | 643.85 | 632.8 | 589.29 | 587.56 | 546.07 | 486.13 | 479.99 | 435.84 | 404.66 | 365.01 |
| D-LaF731 | 模压前 | 1.71948 | 1.72243 | 1.72541 | 1.72625 | 1.72704 | 1.73061 | 1.73077 | 1.73505 | 1.74345 | 1.74452 | 1.75375 | 1.76258 | 1.77834 |
| | 模压后 | 1.71738 | 1.72033 | 1.72331 | 1.72415 | 1.72494 | 1.72851 | 1.72871 | 1.73299 | 1.74133 | 1.74240 | 1.75159 | 1.76042 | 1.77618 |
| D-LaF743 | 模压前 | 1.73365 | 1.73621 | 1.73876 | 1.73948 | 1.74016 | 1.74317 | 1.74330 | 1.74689 | 1.75383 | 1.75470 | 1.76215 | 1.76911 | 1.78110 |
| | 模压后 | 1.73097 | 1.73353 | 1.73608 | 1.73680 | 1.73748 | 1.74049 | 1.74060 | 1.74419 | 1.75111 | 1.75198 | 1.75946 | 1.76642 | 1.77841 |
| D-ZLaF52N | 模压前 | 1.79762 | 1.80084 | 1.80411 | 1.80505 | 1.80590 | 1.80982 | 1.81000 | 1.81469 | 1.82387 | 1.82502 | 1.83510 | 1.84468 | 1.86160 |
| | 模压后 | 1.79494 | 1.79816 | 1.80143 | 1.80237 | 1.80322 | 1.80714 | 1.80734 | 1.81203 | 1.82114 | 1.82229 | 1.83237 | 1.84195 | 1.85887 |
| D-ZLaF52N-M170 | 模压前 | 1.79599 | 1.79921 | 1.80247 | 1.80340 | 1.80427 | 1.80817 | 1.80834 | 1.81303 | 1.82223 | 1.82339 | 1.83343 | 1.84298 | 1.85982 |
| | 模压后 | 1.79331 | 1.79653 | 1.79979 | 1.80072 | 1.80159 | 1.80549 | 1.80568 | 1.81037 | 1.81950 | 1.82066 | 1.83070 | 1.84025 | 1.85709 |
| D-ZLaF52L | 模压前 | 1.79373 | 1.79695 | 1.80022 | 1.80114 | 1.80202 | 1.80594 | 1.80610 | 1.81080 | 1.82002 | 1.82117 | 1.83116 | 1.84062 | 1.85741 |
| | 模压后 | 1.79105 | 1.79427 | 1.79754 | 1.79846 | 1.79934 | 1.80326 | 1.80344 | 1.80814 | 1.81729 | 1.81844 | 1.82843 | 1.83789 | 1.85468 |
| D-ZLaF53 | 模压前 | 1.82052 | 1.82413 | 1.82781 | 1.82884 | 1.82982 | 1.83422 | 1.83441 | 1.83972 | 1.85019 | 1.85152 | 1.86315 | 1.87437 | 1.89451 |
| | 模压后 | 1.81699 | 1.82060 | 1.82428 | 1.82531 | 1.82629 | 1.83069 | 1.83088 | 1.83619 | 1.84661 | 1.84794 | 1.85958 | 1.87080 | 1.89094 |
| D-ZLaF851 | 模压前 | 1.83808 | 1.84154 | 1.84505 | 1.84604 | 1.84697 | 1.85116 | 1.85135 | 1.85639 | 1.86628 | 1.86753 | 1.87838 | 1.88871 | 1.90699 |
| | 模压后 | 1.83525 | 1.83871 | 1.84222 | 1.84321 | 1.84414 | 1.84833 | 1.84849 | 1.85353 | 1.86340 | 1.86465 | 1.87549 | 1.88582 | 1.90410 |