

| | | | | |
|-----------------|---------------|-----------------|---------------|------------------------------|
| H-ZBaF65 | 654397 | $n_d = 1.65412$ | $v_d = 39.68$ | $n_F - n_C = 0.016484$ |
| | | $n_e = 1.65803$ | $v_e = 39.46$ | $n_{F'} - n_{C'} = 0.016678$ |

| Refractive Indices | | |
|--------------------|----------------|-------------|
| | λ (nm) | n_λ |
| n_{2325} | 2325.42 | 1.61564 |
| n_{1970} | 1970.09 | 1.62166 |
| n_{1530} | 1529.58 | 1.62838 |
| n_{1129} | 1128.64 | 1.63471 |
| n_{1064} | 1064.00 | 1.63592 |
| n_t | 1013.98 | 1.63693 |
| n_s | 852.11 | 1.64097 |
| $n_{A'}$ | 768.19 | 1.64383 |
| n_r | 706.52 | 1.64651 |
| n_C | 656.27 | 1.64922 |
| $n_{C'}$ | 643.85 | 1.65000 |
| n_{He-Ne} | 632.80 | 1.65072 |
| n_D | 589.29 | 1.65397 |
| n_d | 587.56 | 1.65412 |
| n_e | 546.07 | 1.65803 |
| n_F | 486.13 | 1.66571 |
| $n_{F'}$ | 479.99 | 1.66668 |
| n_g | 435.84 | 1.67515 |
| n_h | 404.66 | 1.68327 |
| n_i | 365.01 | 1.69784 |

| Constants of Dispersion Formula | |
|---------------------------------|-----------------|
| A_0 | 2.66955809E+00 |
| A_1 | -1.17053780E-02 |
| A_2 | 2.16385159E-02 |
| A_3 | 1.09755393E-03 |
| A_4 | -7.38357886E-05 |
| A_5 | 6.82335888E-06 |

| Density | |
|-----------------------------|------|
| ρ (g/cm ³) | 3.01 |

| Solarization | |
|---------------------|------|
| $\Delta\lambda$ (%) | -1.6 |

| Relative Partial Dispersion | |
|-----------------------------|--------|
| $P_{d,C}$ | 0.2973 |
| $P_{e,d}$ | 0.2372 |
| $P_{g,F}$ | 0.5727 |
| $P'_{d,c'}$ | 0.2470 |
| $P'_{e,d}$ | 0.2344 |
| $P'_{g,F'}$ | 0.5079 |

| Deviation of Relative Partial Dispersions | |
|---|---------|
| $\Delta P_{F,e}$ | -0.0024 |
| $\Delta P_{g,F}$ | -0.0050 |
| $\Delta P_{C,t}$ | 0.0132 |
| $\Delta P_{C,s}$ | 0.0049 |

| Thermal Properties | |
|--|------|
| Tg (°C) | 609 |
| Ts (°C) | 671 |
| T ₁₀ ^{14.5} (°C) | 549 |
| T ₁₀ ¹³ (°C) | 590 |
| $\alpha_{-50/80^\circ C}$ (10 ⁻⁷ /K) | 74 |
| $\alpha_{100/300^\circ C}$ (10 ⁻⁷ /K) | 89 |
| λ (W/(m·K)) | 1.13 |

| Mechanical Properties | |
|---------------------------|-------|
| HK (10 ⁷ Pa) | 565 |
| F _A | 141 |
| E (GPa) | 92.0 |
| G (GPa) | 37.0 |
| μ | 0.243 |
| σ_b (MPa) | 88.3 |
| B (10 ⁻¹² /Pa) | 2.77 |

| Chemical Properties (grade) | |
|-----------------------------|---|
| RC (S) | 1 |
| RA (S) | 1 |
| D _W | 1 |
| D _A | 1 |
| R _{OH} (S) | 1 |
| RP (S) | 1 |

| Expansion Coefficient α (×10 ⁻⁷ /K) | |
|---|----------|
| °C | α |
| -50/-40 | 66 |
| -40/-30 | 69 |
| -30/-20 | 71 |
| -20/-10 | 72 |
| -10/0 | 73 |
| 0/10 | 74 |
| 10/20 | 75 |
| 20/30 | 75 |
| 30/40 | 76 |
| 40/50 | 77 |
| 50/60 | 78 |
| 60/70 | 78 |
| 70/80 | 79 |
| 80/90 | 79 |
| 90/100 | 80 |
| 100/110 | 81 |
| 110/120 | 82 |
| 120/130 | 83 |
| 130/140 | 84 |
| 140/150 | 85 |
| 150/160 | 85 |

| Internal Transmittance | | |
|------------------------|--------------|---------------|
| λ (nm) | τ_{5mm} | τ_{10mm} |
| 2400 | 0.917 | 0.840 |
| 2200 | 0.950 | 0.900 |
| 2000 | 0.987 | 0.974 |
| 1800 | 0.993 | 0.986 |
| 1600 | 0.999 | 0.998 |
| 1400 | 0.999 | 0.998 |
| 1200 | 0.999 | 0.998 |
| 1060 | 0.999 | 0.998 |
| 1000 | 0.999 | 0.998 |
| 950 | 0.999 | 0.998 |
| 900 | 0.999 | 0.998 |
| 850 | 0.999 | 0.998 |
| 800 | 0.999 | 0.998 |
| 750 | 0.999 | 0.998 |
| 700 | 0.999 | 0.998 |
| 650 | 0.999 | 0.998 |
| 600 | 0.999 | 0.998 |
| 550 | 0.999 | 0.998 |
| 500 | 0.999 | 0.998 |
| 480 | 0.998 | 0.996 |
| 460 | 0.997 | 0.994 |
| 440 | 0.996 | 0.992 |
| 420 | 0.994 | 0.990 |
| 400 | 0.991 | 0.983 |
| 390 | 0.988 | 0.974 |
| 380 | 0.977 | 0.958 |
| 370 | 0.957 | 0.919 |
| 360 | 0.899 | 0.813 |
| 350 | 0.751 | 0.568 |
| 340 | 0.401 | 0.164 |
| 330 | | |
| 320 | | |
| 310 | | |
| 300 | | |
| 290 | | |
| 280 | | |

| Coloration Code | |
|--|---------|
| $\lambda_{80}(\lambda_{70})/\lambda_5$ | 370/335 |
| Coloration of Internal Transmittance | |
| $\lambda\tau_{80}/\lambda\tau_5$ | 360/336 |

| Range of Temperature (°C) | Temperature Coefficients of Refractive Index | | | | | | | | | |
|---------------------------|--|-----|-----|-----|-------|-----|-----|-----|-----|-----|
| | dn/dt relative (×10 ⁻⁶ / °C) | | | | | | | | | |
| | t | s | C | C' | He-Ne | d | e | F | F' | g |
| -60 ~ -40 | 2.0 | 2.4 | 2.7 | 2.8 | 2.9 | 3.1 | 3.3 | 3.7 | 3.8 | 4.6 |
| -40 ~ -20 | 2.1 | 2.5 | 2.7 | 2.8 | 2.9 | 3.2 | 3.5 | 3.8 | 3.9 | 4.8 |
| -20 ~ 0 | 2.4 | 2.7 | 2.9 | 2.9 | 3.0 | 3.3 | 3.5 | 3.9 | 3.9 | 4.9 |
| 0 ~ 20 | 2.6 | 2.9 | 3.1 | 3.1 | 3.2 | 3.5 | 3.6 | 4.1 | 4.1 | 4.9 |
| 20 ~ 40 | 2.7 | 3.0 | 3.2 | 3.2 | 3.3 | 3.6 | 3.7 | 4.3 | 4.3 | 5.1 |
| 40 ~ 60 | 2.7 | 3.0 | 3.3 | 3.3 | 3.4 | 3.7 | 4.0 | 4.6 | 4.6 | 5.4 |
| 60 ~ 80 | 2.9 | 3.1 | 3.3 | 3.3 | 3.4 | 3.9 | 4.3 | 4.8 | 4.8 | 5.6 |
| 80 ~ 100 | 3.0 | 3.2 | 3.4 | 3.5 | 3.6 | 4.0 | 4.4 | 5.0 | 5.0 | 5.8 |
| 100 ~ 120 | 3.2 | 3.4 | 3.6 | 3.7 | 3.8 | 4.1 | 4.5 | 5.2 | 5.2 | 6.0 |
| 120 ~ 140 | 3.3 | 3.5 | 3.8 | 3.9 | 4.0 | 4.3 | 4.6 | 5.3 | 5.3 | 6.1 |
| 140 ~ 160 | 3.4 | 3.6 | 3.9 | 4.0 | 4.1 | 4.4 | 4.8 | 5.3 | 5.4 | 6.3 |

| Constants of dn/dt | | |
|--------------------|----------------|----------------|
| D ₀ | D ₁ | D ₂ |
| 1.44E-06 | 1.63E-08 | -2.55E-11 |
| E ₀ | E ₁ | λ_{TK} |
| 5.71E-07 | 3.95E-10 | 2.77E-01 |