

H-ZF50GT	741278	$n_d = 1.74077$	$v_d = 27.76$	$n_F - n_C = 0.026685$
		$n_e = 1.74707$	$v_e = 27.54$	$n_{F'} - n_{C'} = 0.027125$

Refractive Indices		
	λ (nm)	n_λ
n_{2325}	2325.42	1.69064
n_{1970}	1970.09	1.69692
n_{1530}	1529.58	1.70426
n_{1129}	1128.64	1.71195
n_{1064}	1064.00	1.71354
n_t	1013.98	1.71491
n_s	852.11	1.72060
$n_{A'}$	768.19	1.72483
n_r	706.52	1.72888
n_C	656.27	1.73307
$n_{C'}$	643.85	1.73427
n_{He-Ne}	632.80	1.73540
n_D	589.29	1.74054
n_d	587.56	1.74077
n_e	546.07	1.74707
n_F	486.13	1.75976
$n_{F'}$	479.99	1.76139
n_g	435.84	1.77598
n_h	404.66	1.79059
n_i	365.01	1.81850

Constants of Dispersion Formula	
A_0	2.91816811E+00
A_1	-1.22621813E-02
A_2	3.41878382E-02
A_3	2.36117574E-03
A_4	-1.68240994E-04
A_5	2.26673138E-05

Density	
ρ (g/cm ³)	3.05

Solarization	
$\Delta\lambda$ (%)	0.4

Relative Partial Dispersion	
$P_{d,C}$	0.2886
$P_{e,d}$	0.2361
$P_{g,F}$	0.6078
$P'_{d,c'}$	0.2396
$P'_{e,d}$	0.2323
$P'_{g,F'}$	0.5379

Deviation of Relative Partial Dispersions	
$\Delta P_{F,e}$	0.0007
$\Delta P_{g,F}$	0.0103
$\Delta P_{C,t}$	0.0059
$\Delta P_{C,s}$	0.0003

Thermal Properties	
Tg (°C)	616
Ts (°C)	650
T ₁₀ ^{14.5} (°C)	540
T ₁₀ ¹³ (°C)	591
$\alpha_{50/80^\circ C}$ (10 ⁻⁷ /K)	81
$\alpha_{100/300^\circ C}$ (10 ⁻⁷ /K)	101
λ (W/(m·K))	1.16

Mechanical Properties	
HK (10 ⁷ Pa)	555
F _A	143
E (GPa)	90.4
G (GPa)	36.2
μ	0.248
σ_b (MPa)	57.8
B (10 ⁻¹² /Pa)	2.62

Chemical Properties (grade)	
RC (S)	1
RA (S)	1
D _W	1
D _A	1
R _{OH} (S)	1
RP (S)	1

Expansion Coefficient α (×10 ⁻⁷ /K)	
°C	α
-50/-40	72
-40/-30	75
-30/-20	77
-20/-10	78
-10/0	80
0/10	81
10/20	82
20/30	83
30/40	84
40/50	85
50/60	85
60/70	86
70/80	87
80/90	87
90/100	88
100/110	89
110/120	90
120/130	91
130/140	93
140/150	94
150/160	95

Internal Transmittance		
λ (nm)	τ_{5mm}	τ_{10mm}
2400	0.956	0.910
2200	0.969	0.944
2000	0.990	0.980
1800	0.993	0.986
1600	0.998	0.996
1400	0.998	0.996
1200	0.998	0.996
1060	0.998	0.996
1000	0.998	0.996
950	0.998	0.996
900	0.998	0.996
850	0.998	0.996
800	0.998	0.996
750	0.998	0.996
700	0.998	0.996
650	0.998	0.996
600	0.998	0.996
550	0.998	0.996
500	0.996	0.994
480	0.993	0.991
460	0.990	0.988
440	0.987	0.981
420	0.982	0.965
400	0.955	0.914
390	0.914	0.834
380	0.790	0.623
370	0.467	0.219
360		
350		
340		
330		
320		
310		
300		
290		
280		

Coloration Code	
$\lambda_{80}(\lambda_{70})/\lambda_5$	410/365
Coloration of Internal Transmittance	
$\lambda\tau_{80}/\lambda\tau_5$	389/364

Range of Temperature (°C)	Temperature Coefficients of Refractive Index									
	dn/dt relative (×10 ⁻⁶ / °C)									
	t	s	C	C'	He-Ne	d	e	F	F'	g
-60 ~ -40	0.8	1.4	1.8	1.8	1.8	2.1	2.6	3.6	3.6	4.7
-40 ~ -20	0.8	1.4	1.8	1.8	1.9	2.1	2.7	3.7	3.7	5.0
-20 ~ 0	0.9	1.5	1.9	1.9	1.9	2.3	2.7	3.8	3.8	5.2
0 ~ 20	0.9	1.5	1.9	1.9	1.9	2.4	2.8	4.0	4.0	5.4
20 ~ 40	0.8	1.6	1.9	2.0	2.1	2.6	3.1	4.3	4.3	5.8
40 ~ 60	1.0	1.7	2.0	2.1	2.2	2.6	3.1	4.6	4.6	6.0
60 ~ 80	1.2	1.9	2.3	2.3	2.4	2.9	3.2	4.8	4.8	6.3
80 ~ 100	1.4	2.0	2.4	2.5	2.7	3.0	3.4	4.9	4.9	6.6
100 ~ 120	1.4	2.1	2.6	2.7	2.7	3.1	3.6	5.1	5.1	6.8
120 ~ 140	1.5	2.2	2.9	3.0	3.1	3.5	3.8	5.4	5.4	7.1
140 ~ 160	1.7	2.4	3.0	3.0	3.1	3.6	4.0	5.6	5.6	7.3

Constants of dn/dt		
D ₀	D ₁	D ₂
-1.87E-06	1.30E-08	-1.69E-11
E ₀	E ₁	λ_{TK}
8.65E-07	7.76E-10	2.93E-01