

H-ZF52NGT	847238	$n_d = 1.84666$	$v_d = 23.78$	$n_F - n_C = 0.035608$
		$n_e = 1.85504$	$v_e = 23.59$	$n_{F'} - n_{C'} = 0.036247$

Refractive Indices		
	λ (nm)	n_λ
n_{2325}	2325.42	1.78524
n_{1970}	1970.09	1.79201
n_{1530}	1529.58	1.80020
n_{1129}	1128.64	1.80936
n_{1064}	1064.00	1.81133
n_t	1013.98	1.81304
n_s	852.11	1.82028
$n_{A'}$	768.19	1.82573
n_r	706.52	1.83101
n_C	656.27	1.83649
$n_{C'}$	643.85	1.83807
n_{He-Ne}	632.80	1.83956
n_D	589.29	1.84635
n_d	587.56	1.84666
n_e	546.07	1.85504
n_F	486.13	1.87210
$n_{F'}$	479.99	1.87431
n_g	435.84	1.89416
n_h	404.66	1.91418
n_i	365.01	1.95237

Relative Partial Dispersion	
$P_{d,C}$	0.2856
$P_{e,d}$	0.2353
$P_{g,F}$	0.6195
$P'_{d,c'}$	0.2370
$P'_{e,d}$	0.2312
$P'_{g,F'}$	0.5476

Chemical Properties (grade)	
RC (S)	1
RA (S)	1
D_W	1
D_A	1
R_{OH} (S)	1
RP (S)	1

Internal Transmittance		
λ (nm)	τ_{5mm}	τ_{10mm}
2400	0.893	0.928
2200	0.954	0.953
2000	0.994	0.977
1800	0.999	0.985
1600	0.999	0.994
1400	0.999	0.995
1200	0.999	0.996

Deviation of Relative Partial Dispersions	
$\Delta P_{F,e}$	0.0020
$\Delta P_{g,F}$	0.0154
$\Delta P_{C,t}$	0.0032
$\Delta P_{C,s}$	-0.0022

Expansion Coefficient α ($\times 10^{-7}/K$)	
$^{\circ}C$	α
-50/-40	75
-40/-30	78
-30/-20	79
-20/-10	81
-10/0	82
0/10	83
10/20	84
20/30	85
30/40	85
40/50	86
50/60	86
60/70	87
70/80	87
80/90	88
90/100	89
100/110	90
110/120	92
120/130	93
130/140	94
140/150	96
150/160	97

1060	0.999	0.998
1000	0.999	0.998
950	0.999	0.998
900	0.999	0.998
850	0.999	0.998
800	0.999	0.998
750	0.999	0.998
700	0.998	0.997
650	0.998	0.996
600	0.997	0.994
550	0.996	0.992
500	0.991	0.983
480	0.988	0.977
460	0.985	0.970
440	0.978	0.957
420	0.964	0.930
400	0.925	0.855
390	0.863	0.745
380	0.695	0.483
370	0.346	0.120
360		
350		
340		
330		
320		
310		
300		
290		
280		

Thermal Properties	
T_g ($^{\circ}C$)	632
T_s ($^{\circ}C$)	662
$T_{10}^{14.5}$ ($^{\circ}C$)	582
T_{10}^{13} ($^{\circ}C$)	608
$\alpha_{50/80^{\circ}C}$ ($10^{-7}/K$)	83
$\alpha_{100/300^{\circ}C}$ ($10^{-7}/K$)	101
λ (W/(m·K))	1.04

Mechanical Properties	
HK (10^7Pa)	531
F_A	176
E (GPa)	96.1
G (GPa)	38.1
μ	0.262
σ_b (MPa)	56
B ($10^{-12}/Pa$)	2.54

Constants of Dispersion Formula	
A_0	3.25093122E+00
A_1	-1.35032313E-02
A_2	4.90304607E-02
A_3	2.49344608E-03
A_4	-1.81762799E-05
A_5	1.94686410E-05

Density		Solarization	
ρ (g/cm ³)	3.54	$\Delta\lambda$ (%)	-1.1

Range of Temperature ($^{\circ}C$)	Temperature Coefficients of Refractive Index									
	dn/dt relative ($\times 10^{-6} / ^{\circ}C$)									
	t	s	C	C'	He-Ne	d	e	F	F'	g
-60~-40	-1.0	-0.9	0.0	0.5	0.5	0.7	1.0	1.6	1.7	3.0
-40~-20	-0.9	-0.9	0.0	0.5	0.6	0.8	1.1	1.9	2.0	3.6
-20~0	-0.7	-0.8	0.1	0.5	0.6	0.9	1.3	2.4	2.5	4.0
0~20	-0.7	-0.7	0.2	0.6	0.7	0.9	1.4	2.7	3.1	4.4
20~40	-0.7	-0.6	0.4	0.7	0.7	1.0	1.6	3.1	3.7	4.8
40~60	-0.7	-0.6	0.4	0.7	0.7	1.0	1.9	3.5	4.0	5.3
60~80	-0.7	-0.6	0.4	0.7	0.8	1.2	2.1	3.8	4.3	5.7
80~100	-0.6	-0.6	0.5	0.7	0.8	1.3	2.1	4.1	4.6	6.1
100~120	-0.6	-0.5	0.5	0.8	0.9	1.3	2.2	4.4	4.8	6.5
120~140	-0.6	-0.4	0.7	0.8	1.0	1.5	2.3	4.7	5.0	6.9
140~160	-0.7	-0.4	0.8	0.9	1.1	1.9	2.5	5.1	5.4	7.2

Coloration Code	
$\lambda_{80}(\lambda_{70})/\lambda_5$	(399)/369
Coloration of Internal Transmittance	
$\lambda\tau_{80}/\lambda\tau_5$	395/368

Constants of dn/dt		
D_0	D_1	D_2
-5.25E-06	7.18E-09	-2.89E-11
E_0	E_1	λ_{TK}
1.16E-06	2.39E-09	2.61E-01