

H-ZK21		623581	n _d = 1.62299		v _d = 58.12		n _F − n _C = 0.010719		
			n _e = 1.62555		v _e = 57.87		n _{F'} − n _{C'} = 0.010809		
Refractive Indices			Relative Partial Dispersion		Chemical Properties (grade)		Internal Transmittance		
	λ (nm)	n _λ					λ (nm)	τ5mm	τ10mm
n ₂₃₂₅	2325.42	1.59235					2400	0.882	0.778
n ₁₉₇₀	1970.09	1.59795					2200	0.948	0.899
n ₁₅₃₀	1529.58	1.60402					2000	0.980	0.960
n ₁₁₂₉	1128.64	1.60931					1800	0.988	0.976
n ₁₀₆₄	1064.00	1.61026	1600	0.999	0.998				
n _t	1013.98	1.61103	1400	0.999	0.998				
n _s	852.11	1.61401	1200	0.999	0.998				
n _{A'}	768.19	1.61603	1060	0.999	0.998				
n _r	706.52	1.61787	1000	0.999	0.998				
n _C	656.27	1.61973	950	0.999	0.998				
n _{C'}	643.85	1.62025	900	0.999	0.998				
n _{He-Ne}	632.80	1.62074	850	0.999	0.998				
n _D	589.29	1.62290	800	0.999	0.998				
n _d	587.56	1.62299	750	0.999	0.998				
n _e	546.07	1.62555	700	0.999	0.998				
n _F	486.13	1.63045	650	0.999	0.998				
n _{F'}	479.99	1.63106	600	0.999	0.998				
n _g	435.84	1.63629	550	0.999	0.998				
n _h	404.66	1.64113	500	0.999	0.998				
n _i	365.01	1.64946	480	0.999	0.998				
			460	0.999	0.998				
			440	0.999	0.998				
			420	0.996	0.992				
			400	0.992	0.985				
			390	0.988	0.976				
			380	0.982	0.965				
			370	0.962	0.926				
			360	0.924	0.854				
			350	0.850	0.723				
			340	0.698	0.487				
			330	0.421	0.177				
			320	0.071	0.005				
			310						
			300						
			290						
			280						
	</								